

Effect of Sm^{3+} as co-dopant in $\text{CaSO}_4:\text{Dy,P}$ TLD phosphor

J.A.Wani¹, N.S. Dhoble[#] and S.J.Dhoble^{1*}

¹Department of Physics, RTM Nagpur University, Nagpur-440033, India

[#]Department of Chemistry, Sevadal College, Sakkardara, Nagpur-440009, India

Abstract

$\text{CaSO}_4:\text{Dy,P}$ and $\text{CaSO}_4:\text{Dy,P,Sm}$ thermoluminescence (TL) phosphors have been prepared by acid method and their TL glow curves and photoluminescence (PL) excitation and emission spectra are recorded. PL emission bands at 565, 599 and 613 nm were observed for $\text{CaSO}_4:\text{Dy,P,Sm}$ under the excitation wavelength 402 nm. Dosimetric peak is observed around 246°C at high temperature. Co-doping of Sm^{3+} in $\text{CaSO}_4:\text{Dy,P}$ enhances its TL intensity by a factor of 1.11.

Keywords: Thermoluminescence, phosphor; $\text{CaSO}_4:\text{Dy,P}$; photoluminescence

INTRODUCTION

Singly doped CaSO_4 phosphors have been studied in detail in the past[1]. Rare earths, especially Dy or Tm doped CaSO_4 thermoluminescent phosphors are widely used in radiation dosimetry. Two models have been proposed for the thermoluminescence (TL) mechanism in CaSO_4 based thermoluminescent phosphors. Nambi et al. extended the model based on redox reactions proposed by Merz and Pershan for $\text{CaF}_2:\text{RE}$ phosphors as well as Nambi et al. also suggested another model (energy transfer model), which was later supported by Morgan and Stoebe [2-10]. Tomita and Tsutsumi showed that the TL emission spectrum of pure CaSO_4 has a maximum at about 335 nm. According to the energy transfer model, there is no direct recombination at the RE site but the energy of electron-hole recombination is transferred to RE^{3+} . However, no direct proof has been reported so far[11-18]. In the present study, in addition to change in surface morphology, considerable improvement has been observed in the case of thermoluminescence intensity of the as prepared phosphors. This can be seen from the comparison graph of standard $\text{CaSO}_4:\text{Dy}$ and $\text{CaSO}_4:\text{P,Dy,Sm}^{3+}$ phosphors. It is worth mentioning here that thermoluminescence(TL) intensity is 1.11 times greater in case of $\text{CaSO}_4:\text{P,Dy,Sm}^{3+}$ phosphors prepared via slightly modified acid distillation method than standard $\text{CaSO}_4:\text{Dy}$ TLD phosphor. The photoluminescence (PL) characteristics of almost all phosphors are also good though slight variations have been observed. In this paper, the effect of co-doping $\text{CaSO}_4:\text{Dy,P}$ with Sm is investigated .

EXPERIMENTAL

For the preparation of $\text{CaSO}_4:\text{Dy,P,Sm}$ phosphors all starting materials used were of analytical grade. $\text{CaSO}_4:\text{Dy,P,Sm}$ phosphors were prepared by following the method described by Yamashita et al. The sample phosphors thus prepared were repeatedly washed with double distilled water to remove the traces of acid. Phosphors were annealed at 973 K. The concentration of P used was 1mol%. The concentration of Dy^{3+} used was 0.1mol% but concentration of Sm ion(s) was varied from 0.05mol% to 0.5mol%. The maximum thermoluminescence (TL) intensity was observed for the composition 1mol%P, 0.1mol%Dy³⁺ and 0.1mol% Sm³⁺.

The photoluminescence (PL) emission and excitation spectra of the samples were recorded by using a RF-5301PC

SHIMADZU Spectrofluorophotometer. TL glow curves were recorded with the usual set up Nucleonix (TL-1009) Reader. SEM micrographs were obtained using JEOL,6380A Scanning Electronmicroscope.

RESULTS AND DISCUSSION

Photoluminescence Characteristics

Photoluminescence emission spectra fig.1 of $\text{CaSO}_4:\text{Dy,P,Sm}$ phosphor under excitation wavelength 402 nm(${}^6\text{H}_{5/2} \rightarrow {}^4\text{F}_{7/2}$) , sharp emission peaks are observed at 565nm and 599 nm emission wavelength. The emission spectra observed at excitation wavelength 402 nm consists of 565 nm (${}^4\text{G}_{5/2} \rightarrow {}^6\text{H}_{5/2}$), 599 nm (${}^4\text{G}_{5/2} \rightarrow {}^6\text{H}_{7/2}$) and 613 nm (${}^4\text{F}_{3/2} \rightarrow {}^6\text{H}_{9/2}$) respectively. The dominant transitions are ${}^4\text{G}_{5/2} \rightarrow {}^6\text{H}_{5/2}$ (565 nm) and ${}^4\text{G}_{5/2} \rightarrow {}^6\text{H}_{7/2}$ (599 nm)[2,3]




Fig 1. Photoluminescence emission spectra of $\text{CaSO}_4:\text{Dy,P,Sm}$ phosphor. Emission spectra consist of 565, 599 and 613 nm wavelengths observed at 402 nm excitation wavelength.

Thermoluminescence(TL) Characteristics

Figure 2 shows the typical TL glow curves of the $\text{CaSO}_4:\text{Dy,P,Sm}$ phosphors exposed to gamma radiations from ${}^{60}\text{Co}$ source at room temperature. Thermoluminescence of the phosphor materials was recorded using Nucleonix TLD reader. The TL characteristics of the as prepared phosphors are nearly similar to the TL characteristics of the standard $\text{CaSO}_4:\text{Dy}$ TLD phosphor. The TL intensity of the phosphor material prepared by slightly modified acid distillation method is 1.11 times greater than the standard $\text{CaSO}_4:\text{Dy}$ TLD phosphor. This is really significant improvement observed in TL intensity. Hence it seems reasonable to suggest that there is some degree of sensitization taking place in $\text{CaSO}_4:\text{Dy,P,Sm}$ phosphors. Fig.3 depicts the intensity wise comparison between

standard and as prepared phosphors. No doubt contribution to thermoluminescence from intrinsic defects present in the CaSO_4 lattice is enhanced by the addition of rare-earths but some recent investigations suggest that change in surface morphology of the bulk material can also prove effective.




Fig 2. TL glow curves of $\text{CaSO}_4:\text{Dy,P,Sm}$ ($\text{P}=1\text{mol}\%$; $\text{Dy}=0.1\text{mol}\%$; $\text{Sm}=0.05, 0.1, 0.5\text{mol}\%$) phosphor exposed to gamma radiations from ^{60}Co source at room temperature.

Fig3. Comparison for glow curves of standard $\text{CaSO}_4:\text{Dy}$ TLD phosphor, $\text{CaSO}_4:\text{Dy,P}$; $\text{CaSO}_4:\text{Dy,P,Sm}$ ($\text{P}=1\text{mol}\%$; $\text{Dy}=0.1\text{mol}\%$; $\text{Sm}=0.1\text{mol}\%$) phosphors.

SEM micrographs of $\text{CaSO}_4:\text{Dy,P,Sm}$ phosphors.




Fig 4. SEM micrographs of $\text{CaSO}_4:\text{Dy,P,Sm}$ phosphors

From the micrograph (Fig.4) it can be seen that particles of $\text{CaSO}_4:\text{Dy,P,Sm}$ have shaped like long bars with porous type surfaces and with appreciable diameter. This is obviously different from the morphological characteristics of $\text{CaSO}_4:\text{Dy}$ and $\text{CaSO}_4:\text{Dy,P}$ reported till date. Since thermoluminescence is very complicated process it is not yet clear if this morphological change has made any impact on TL of this phosphor. It is to be pointed out here that particle size in each case falls in the micro range which is considered very favorable for thermoluminescence characteristics of a phosphor material. Recently, some nano-TL phosphors have also been reported. These nano-phosphors are suggested to have possible applications in dosimetry of heavy charged particles [18-20].

CONCLUSION

Rod type structures of $\text{CaSO}_4:\text{Dy,P,Sm}$ phosphors have been obtained. As expected, characteristic photoluminescence emission and excitation spectra been observed for Sm^{3+} in $\text{CaSO}_4:\text{Dy,P,Sm}$ phosphors. Co-doping of Sm^{3+} in $\text{CaSO}_4:\text{Dy,P}$ phosphor increases the TL intensity by a factor of approximately 1.11.

Only TL intensity of 246 °C peak has increased.

ACKNOWLEDGEMENT

Authors are grateful to Board of Research in Nuclear Sciences (BRNS), Department of Atomic Energy, Govt. of India, for providing financial assistance to carry out this work under research project (sanctioned letter No. 2011/37P/10/BRNS/144) .

REFERENCES

- [1] S.N. Menon, S.S. Sanaye, B.S. Dhabekar, R. Kumar, B.C. Bhatt; 2005. *Radiat. Measure.* 39:111
- [2] A.R. Lakshmanan ; Prog. 1991. *Mat. Sci.* 44:1
- [3] M.D. Morgan, T.G. Stoebe; 1989. *J Phys: Condens. Matter* 1:5773
- [4] V.N. Bapat ;1977. *J Phys C: Solid St Phys* 10:465.
- [5] A.R. Lakshmanan, B. Chandra, R.C .Bhatt; 1978. *Nucl Instrum Meth* 153.
- [6] S.J. Dhoble, S.V. Moharil, T.K.Gundu Rao ; 2001. *J. Lumin* 93:49
- [7] Y. Wang, N.Can , P.D.Townsend ;2011. *J. Lumin.* 131:186
- [8] T.Yamashita, N.Nadah,O.Hnishi, S.Kitamura ; 1971. Proc. 2nd Inter Conf. Lum. Dosim. *Health Phys.* 21:295
- [9] M. Prockien ; 1978.*Nuclear Instrum. and Methods* 151:603
- [10] K. Mori, Y. Kojima, N. Nishimiya ;2011. *J. Ceramic Soc. Japan* 119:587
- [11] A.R. Lakshmanan ; 1992. *Radiat Prot Dosim.* 41:42
- [12] M. Zahedifar, M. Mehrabi, S. Harooni; 2011. *Appli. Radiat. and Isotopes* 69:1002
- [13] D. Lapraz, H. Prevost, A. Baumer, P. lacconi, M. Benabdessalm, P.Blanc ; 2000. *Phys. Status Solidi A* 181:515.
- [14] S. J. Dhoble, S.V. Moharil, T.K. Gundu Rao ; 2001. *J. Lumin.* 93:43
- [15] A. K. Bakshi, B.S.Sanyal, V.J. Joshi, M.K.Bhide, V.Natarajan, A.Sharma; 2011.*Appli. Radiat.and Isotopes* 69:254
- [16] S.J. Dhoble, S. V. Moharil, S. M. Dhopte, P. L. Muthal,V. K. Kondawar ; 1993. *Phys. stat. sol. (a)* 135:289
- [17] A.K. Bakshi, B. Sanyal , V.J. Joshi , M.K. Bhide , V. Natarajan, A. Sharma; 2011. *Appli. Radiat. and Isotopes* 69:254
- [18] A. Choubey, S.K. Sharma , S.P. Lochab , T. Shripathi ; 2011. *Physica B* 406:4483
- [19] A. Choubey, S. K.Sharma , S.P.Lochab , D.Kanjilal ; 2011. *J. Lumin.* 131:2093
- [20] N. Salaha, P.D. Sahare, S.P. Lochab, P. Kumar; 2006. *Radia. Measure.* 41:40